

Elite 2.0

Closed Cell, medium density HFO blown spray foam

ELITE 2.0 is a medium density spray-applied rigid polyurethane foam system insulation formulated without ozone depletion substances (Zero ODS). ELITE 2.0 is made with **HFO** and has a global warming potential (GWP) of 1, which is 99.9% lower than current HFC used in this industry. The product complies with the International Code Council's AC377 standard and obtains high ranked results to ASTM E84 fire testing. It is a high-performance insulation and air barrier, ideal for new construction and retrofit insulation of residential and commercial buildings.

ELITE 2.0 is lime green in colour.

TYPICAL PHYSICAL PROPERTIES

PHYSICAL PROPERTIES	STANDARD	RESULT
Aged R-Value (90 days/140°F)	ASTM C518	6.8 @ 1" 23.2 @ 3.5"
Core Density	ASTM D1622	2.00 lb/ft ³
Compressive Strength	ASTM D1621	26 psi
Tensile Strength	ASTM D1623	29 psi
Water Vapour Permeance	ASTM E96	0.73 perm
Water Absorption	ASTM D2842	< 2%
Fungi Resistance	ASTM C1338	Nogrowth
Closed Cell Content	ASTM D2856	>98%
Dimensional Stability (14 days 70°C, 97±3% RH)	ASTM D2126	3 %
Air Leakage (75 Pa @ 1")	ASTM E283M	< 0.02 L/sm ²

FIRE PERFORMANCE CHARACTERISTICS

ASTM E 84	Surface Burning Characteristics, 4" Thick Flame Spread Index Smoke Developed	Class1 10 280
AC 377 Appendix X	Without a coating	Meets Criteria
NFPA 286	With 15 mils (dry) DC-315	Meets Criteria



PREMIUM PRODUCT

Genyk uses the highest-grade raw materials and state-of-the-art manufacturing facilities. The result is a durable product with industry leading thermal resistance



SUSTAINABILITY

Elite 2.0 is non-toxic HFO based and formulated with recycled products, captured rainwater and plant-based materials. Environmentally responsible behaviour is a Genyk standard.



CERTIFIED QUALITY



Genyk maintains thorough in-house quality control. In addition, Elite 2.0 is tested and certified by **ICC-ES #ESR-5150**, including fire protection certifications Appendix X and NFPA 286

COMPONENT PRODUCT SPECIFICATIONS

PROPERTIES	A - PMDI ISOCYANATE	ELITE 2.0 RESIN
Colour	Brown Liquid	Green Liquid
Viscosity at 25°C	150 – 250 cps	300 – 800 cps
Specific Gravity at 25°C	1.22 – 1.25	1.17 – 1.22
Shelf Life	12 months	6 months
Storage Temperature	50°F - 100°F	50°F - 77°F
Ratio (volume)	100	100

INSTALLATION GUIDELINES

ELITE 2.0	Ambient Temperatures	Spray Temperatures	Minimum Spray Pressure
Summer	45°F to 95°F	105°F - 120°F	800 psi
Inter	30°F to 70°F	110°F - 130°F	800 psi
Winter	15°F to 60°F	110°F - 130°F	800 psi

Processing conditions can vary depending on temperature, humidity, substrate, equipment, and other factors. It is the applicator's responsibility to process and apply **Elite 2.0** within specification.



During the application, it is important not to exceed 2 inches per pass, in order not to alter the quality of the foam.



Before handling these chemicals, please consult the Safety Data Sheet for the two components, that are available from Genyk.

ADDITIONAL INFORMATION

- Maximum Pass Thickness: 2" (to avoid fire hazards resulting from excessive heat generation)
- Dual Pass thickness: 2" + 2"
- Internal temperature of installed pass must be 85°F before installing subsequent passes. Maximum thickness during 24-hour period is 203mm (8 inches).
- The service temperature of Elite 2.0 is between -76°F°C and 176°F.
- Recommended storage temperature of materials is from 50°F to 77°F.
- See ICC-ES Evaluation Report No. **ESR-5150** at www.icc-es.org

The information contained herein is based on information available to Genyk Inc. The data is considered an accurate description of the product performance and is presented in good faith. However, Genyk Inc. disclaims any liability for incidental or consequential damages which may result from the inappropriate use of this product. It is the user's responsibility to thoroughly test the product in any application to determine performance, efficiency and safety. No information contained herein is to be considered as permission or recommendation to infringe on any patent or other intellectual property.