

TO **Mike Richmond**
EMAIL **mikerichmond@genyk.com**
Genyk Polyurethane Solution
1701, 3rd Avenue
Shawinigan QC G9T 2W6

R-24023.000
Genyk – Unvented Spray Foam
Roof Assembly Assessment

DATE November 20, 2020

REGARDING **Hygrothermal Assessment of an Unvented Spray Foam Roof Assembly. – FINAL DRAFT**

Dear Mr. Richmond,

As requested, RDH Building Science Laboratories (RDH) is pleased to provide you with this report for an assessment of an unvented spray foam roof assembly. Concerns have been raised regarding moisture related issues at the interior surface of the foam within the assembly. A dew point analysis will be conducted to determine the risk of moisture accumulation at the surface of the foam.

1 Roof Assembly

The roof assembly in question is constructed using a scissor truss, so a void space occurs between the interior gypsum and the underside of the spray foam that is installed directly to the underside of the roof sheathing. The assembly is as follows from the exterior, to the interior.

- Roof cladding – asphalt shingles or metal roof
- Roofing underlay
- Roof sheathing – OSB or plywood
- R30 minimum 2pcf closed cell spray polyurethane foam (ccSPF) directly applied to the underside of the roof sheathing around the framing.
- Void Space
- No vapour barrier
- Interior ceiling drywall with latex paint.

2 Hygrothermal Analysis

To conduct an analysis of the moisture condensation and risk at the surface of the spray foam, the R-values of every layer in the enclosure was determined, based on material properties found in the 2017 ASHRAE Handbook of Fundamentals, a current industry standard. The R-values used in this analysis are shown in Table 2.1. The R-value ratio to the interior and the exterior of the surface of the spray foam is determined. In this case, There is R32 to the exterior of the surface of the spray foam, and there is approximately R2 to the interior of the spray foam including the interior surface film, the drywall, and the air space between the drywall and the spray foam. The R-value ratio determines the temperature at the surface of the spray foam depending on the interior and exterior temperature conditions.

TABLE 2.1 ASSEMBLY R-VALUES (2017 ASHRAE HOF)	
COMPONENT	R-VALUE [FT ² · °F · H/BTU]

Exterior surface film	0.17
Shingles	0.21
Roofing underlay	~0
Roof sheathing	0.62
Closed cell spray foam	31 ¹
Air space (approximate)	1
Interior Drywall	0.45
Interior Surface Film	0.68
R-value exterior of spray foam surface	R32
R-value interior of spray foam surface	R2

Using the calculated R-values to the interior and exterior of the surface of spray foam, the surface temperature of the spray foam can be calculated for a range of exterior temperatures and a constant interior 22°C as shown in Table 2.2.

TABLE 2.2 TEMPERATURE OF SPRAY FOAM FOR A RANGE OF EXTERIOR TEMPERATURES (INTERIOR TEMPERATURE IS 22°C)	
EXTERIOR TEMPERATURE [°C]	TEMPERATURE OF THE INTERIOR SURFACE OF SPRAY FOAM
0	20.6°C
-10	20.0°C
-20	19.4°C
-30	18.8°C
-40	18.1°C
-50	17.5°C
-60	16.9°C

Winter time design temperatures from the 2015 OBC SB-1 Climatic and Seismic Data for some representative cities is shown in Table 2.3. The January 1% design temperature is defined as the lowest temperature at or below which only 1% of the hourly outside air temperatures in January occur.

TABLE 2.3 2015 OBC SB-1 CLIMATIC AND SEISMIC DATA	
CITY	JANUARY 1% DESIGN TEMPERATURE
Windsor	-18°C
Toronto	-20°C
Ottawa	-27°C
Barrie	-26°C
Thunder Bay	-33°C
Kenora	-35°C

Table 2.3 shows the exterior design air temperature, but the roof surface temperature could be decreased by 10-20 degrees at nighttime as a result of night sky radiative

¹ 2016 OBC SB-12 Energy Efficiency for Housing Requires R-31 in ceilings without attic space.

cooling. This occurs when surfaces that are exposed to the sky, experience radiative heat transfer with outer space, cooling surfaces past the air temperature.

2.1 Boundary Conditions

One of the key performance criteria for building enclosure systems in cold climates is the winter time interior relative humidity. The recommended maximum interior RH in Ontario during the winter is 35%, and in colder parts of Canada, the recommended maximum is less. For this analysis we used an interior temperature of 22C, and an interior RH of 40% to provide some safety factor to the analysis. These interior conditions result in an interior dew point of approximately 8C. This means that if the surface of the foam were to approach 8C, then the relative humidity would increase and if the surface were to reach 8C, it may be possible to see condensation on the surface of the foam.

3 Conclusions

When the calculated surface temperatures of the spray foam for exterior temperatures as cold as -60°C are compared to the 8°C dew point of the interior space, it is clear that there is no risk of condensation or moisture accumulation on the surface of the foam or within the interstitial space between the ceiling drywall and spray foam.

4 Assumptions

This analysis and recommendations are based on a few assumptions as listed here.

- The winter time interior relative humidity is kept to a recommended level. In Ontario, this is a maximum of 35%.
- The spray foam is installed in a continuous manner without voids, and in compliance with CAN/ULC S705.2
- Any wood to wood connections that pass through the spray foam layer are air sealed to prevent interior air from passing between them.
- No interior vapour barrier is installed on the exterior of the interior drywall.

If you have any questions after reviewing our analysis, please do not hesitate to contact us by phone or email.

Yours truly,

Jonathan Smegal | M.A.Sc.
Associate, Senior Project Manager
jsmegal@rdh.com
T 519-342-4731
RDH Building Science Inc.

Reviewed by
Aaron Grin | M.A.Sc., P.Eng.
Principal, Building Science
Specialist
agrin@rdh.com
T 519-342-4731
RDH Building Science Inc.

encl.