

December 15, 2020

## **TECHNICAL BULLETIN #137**

### 1. ADHESION of GENYK 'Boreal Elite' to self-adhesive SBS Modified Bitumen Membranes—

The adhesion of GENYK 'Boreal Elite' to several self-adhesive SBS Modified Bitumen Membranes has been determined to exceed the GENYK Air Barrier System separation threshold of 16psi (110kPa).

#### MATERIALS THAT ARE GENYK COMPATIBLE—

1. HENRY –  
Blueskin SA, Blueskin SA LT, Blueskin VP160, Blueskin TWF
2. SOPREMA –  
Soprasedal Stick 1100T, Soprasedal Stick 130, Soprasedal Stick 130S, Soprasedal WFM
3. W.R. MEADOWS –  
Air-Shield, Air Shield TWF
4. 3M-  
3M-3015

### 2. ADHESION of GENYK 'Boreal Elite' to liquid applied Synthetic Rubber Membranes—

The adhesion of GENYK 'Boreal Elite' to several liquid applied SBS Modified Bitumen Membranes has been determined to exceed the CUFGA Air Barrier System separation threshold of 16psi (110kPa).

#### MATERIALS THAT ARE GENYK COMPATIBLE—

1. HENRY –  
AirBloc 06, AirBloc 21, AirBloc 31MR, AirBloc 32MR
2. SOPREMA –  
Soprasedal LM200S, Soprasedal LM200T

*Mike Richmond*

Building Science Specialist



1701, 3e Avenue  
Grand-Mère, Qc  
G9T 2W6

226-339-3089

[mikerichmond@genyk.com](mailto:mikerichmond@genyk.com)

[www.genyk.com](http://www.genyk.com)

